



Comparative Study on Color Stability of Denture Reline Polymers when Using Microwave and Chemical Disinfection

**Farhat Jabeen^{1*}, Rajeev Gupta¹, Archana Nagpal¹, Vishal Katna¹,
Vishwas Mahajan¹ and Pragma Bali¹**

¹Department of Prosthodontics, Himachal Dental College, H.P. (175002), India.

Authors' contributions

The work was carried out in collaboration among all authors. All authors read and approved the final manuscript.

Article Information

DOI: 10.9734/JAMMR/2019/v29i530085

Editor(s):

(1) Dr. Sinan INCE, Department of Pharmacology and Toxicology, University of Afyon Kocatepe, Turkey.

Reviewers:

(1) Janti Sudiono, Trisakti University, Jakarta, Indonesia.

(2) K. Srinivasan, Dr. Ntr University of Health Sciences Vijayawada, Andhra Pradesh, India.

Complete Peer review History: <http://www.sdiarticle3.com/review-history/48257>

Original Research Article

Received 23 December 2018

Accepted 25 March 2019

Published 03 April 2019

ABSTRACT

This study investigated the color stability of reline resin after two methods of disinfection i.e microwave disinfection and chemical disinfection. A stainless steel mold with a breakaway compartment (10 mm in diameter by 0.7 mm thickness) was made to fabricate specimens of various resins. Each material was mixed according to manufacturer's instructions and applied into the mold. Prior to color stability testing, specimens were cleaned in distilled water for 20 minutes to kill any microorganisms that may had contaminated the discs during fabrication. And then specimens were immersed in Sodium Perborate Monohydrate 200 ml of solution for 15 days and microwaved for 15 days so that it is comparable to chemical disinfection soaking. The color stability of each specimen was measured again using spectrophotometer and values were obtained. The data of ΔE , ΔL , Δb , Δa were analysed by 2 way repeated measures ANOVAs test. Significant statistic changes in color parameters ΔL , Δa , Δb of the reline resin DPI, Ufi Gel Hard And Kooliner were observed when dentures were disinfected by Sodium Perborate Monohydrate 2% solutions. The color stability of the reline resin was influenced by time, regardless of disinfection or non disinfection. This can be attributed to bleaching (whitening) effect of reline material. Discoloration

*Corresponding author: E-mail: drfarhatraza27@gmail.com, Farhatraza27@gmail.com;

of resin based materials may be caused by intrinsic or extrinsic factors. Intrinsic factors are related to internal alterations in material resulting from physicochemical reactions or residual monomer oxidation with time. Thus the initiator, quantity and type of monomer and the polymerisation efficiency can affect the color stability of resin based materials. The color stability deviation value ΔE significantly increased to maximum for chemical disinfectant, least for Control group and intermediate for microwaved group. Ufi Gel showed the highest deviation ΔE and Control Group showed the lowest deviation according to results.

Keywords: Color stability of relined resin; microwave disinfection; chemical disinfection; spectrophotometer; dentures; sodium perborate.

1. INTRODUCTION

The fit of dentures continuously break down with time in the supporting tissue. Hard chairside relined resins are utilized for transitory or lasting enhancement of denture fit [1]. Schou et al. and Blair et al. commented that denture stomatitis was a common condition among elderly and was related to continuous denture wearing and poor hygiene [2]. Continuous swallowing or aspiration of microorganisms from dental plaque, which may deteriorate the oral health of patient [3,4]. Dental prostheses brought into a dental office for relining or modifications are sullied with pathogenic microorganisms [5]. Concern about transmission of these organisms between the workplace and research facility has prompted restored enthusiasm for sanitization and disinfection [6]. Current built up strategies have not been ended up being totally viable in averting or taking out the event of denture stomatitis [7]. Therefore, elective disinfection techniques are being sought after, including the utilization of microwave energy and chemical disinfection. Microwave energy has been prescribed for cleaning complete dentures to counteract or treat denture stomatitis and to control cross-contamination [8,9]. The specimens were immersed in 200 ml of water and irradiated with 430 W for 2 minutes [10]. The disinfection method was repeated in different interval which was divided from Day 0 to 15 which is equivalent into 1 year of disinfection required under natural conditions. Specimens were submitted to daily chemical disinfection by immersing into 3.8% Sodium Perborate Monohydrate solution for 15 days and for each soaking, fresh Sodium Perborate Monohydrate solution was used and distilled water was changed daily [11]. This cycle was repeated for 15 days, so that period of chemical disinfection was comparable with that of microwave disinfection and control groups.

Albeit chemical disinfection has been generally suggested, it is conceivable that specific parts of

the disinfectant arrangements may infiltrate the material and not be totally disposed of by rinsing [12,13] Although the disinfectant arrangements utilized in this examination have been shown for denture biofilm control, patients ought to be educated concerning the likelihood of relined materials recoloring in long haul, paying little mind to the utilization or not of disinfectant arrangements [14,15]. Esthetics is an important aspect in denture relining as color of relining material and denture base should match [16]. Despite the wide utilization of both the materials for purification, no similar investigation between the previously mentioned two techniques has been done [17]. However, past examinations have not been reliable or express regarding the approach utilized.

2. METHODOLOGY

This *in vitro* study was conducted to compare the Color Stability of Denture Reline Polymers using Microwave and Chemical Disinfection. A stainless steel mold with a breakaway compartment (10 mm in diameter by 0.7 mm thickness) was made to fabricate specimens of various resins.(ADA specification no. 19). 10 specimens of each resin were prepared under aseptic conditions. Each material was mixed according to manufacturer's instructions and applied into the mold, which were placed on an acetate sheet and glass slab was placed over the material, and light pressure was applied to remove the excess material from the mold. Specimens were divided into three test groups.

Table 1. Grouping of Samples according to material used

Group	Material used
G1	Kooliner Sample
G2	Ufi Gel Hard Sample
G3	DPI Sample



Fig. 1. Stainless Steel Die (ADA Specification no. 19)



Fig. 2. Example of Grouping of Sample of each material



Fig. 3. Materials used, die and armamentarium

Table 2. Grouping of samples according to microwave disinfectant method used

Group	Non microwaved	Microwaved
G1 (Kooliner)	Control Group G1C	Microwaved Group G1M
G2 (Ufi Gel)	Control Group G2C	Microwaved Group G2M
G3 (DPI)	Control Group G3C	Microwaved Group G3M

Table 3. Grouping of Samples according to Chemical Disinfectant method

Group	Chemical disinfectant
Kooliner G1	Chemically disinfected G1D
Ufi gel G2	Chemically disinfected G2D
DPI G3	Chemically disinfected G3D



Fig. 4. Sample placed in microwave for 2 min at 430 W



Fig. 5. Spectrophotometer Color Guide 45/0 used for Sample testing

Prior to color stability testing, specimens were cleaned in distilled water for 20 minutes to kill any microorganisms that may have contaminated the discs during fabrication. And then specimens were immersed in Clinsodent (Sodium Perborate Monohydrate) 200 ml of solution for 15 days. In test group (G1C, G2C, G3C) Specimens were submitted to daily chemical disinfection by immersing into 3.8% Sodium Perborate Monohydrate solution for 15 days and for each soaking, fresh Sodium Perborate Monohydrate solution was used and distilled water was changed daily. The specimens were immersed in 200 ml of water and irradiated with 430 W for 2 minutes. The microwave cycles were also repeated for 15 days, so that period of chemical disinfection was comparable with that of microwave disinfection and control groups.

The color stability of each specimen was measured again using spectrophotometer and values were obtained. The data of ΔE , ΔL , ΔB , Δa were analysed by 2 way repeated measures ANOVAs test.

All the procedure were done by single operator to avoid any bias. All the experimental groups were then examined under spectrophotometer according to the CIE L*A*B* color order system of Commission International Del' Eclairage [18,19].

3. RESULTS

For DPI Group Descriptive statistics of different colour stability parameters (ΔL , Δa , Δb and ΔE) were attained in Control group, microwave treatment and chemical treatment at 15th day after immersion with DPI. All parameters

appeared significant when compared across control, chemical and microwave group. Chemical disinfectant and Control group showed the highest and lowest deviation respectively. In case of Kooliner Group the value as compared with control were non-significant. Other multiple comparison values were found significant. Chemical disinfectant and Control group showed the highest and lowest deviation respectively. For UFI Gel hard Group chemical disinfectant and control group showed the highest and lowest deviation respectively. Significant statistic changes in color parameters ΔL , Δa , Δb of the reline resin DPI, Ufi Gel Hard And Kooliner were observed when dentures were disinfected by Sodium Perborate Monohydrate 2% solutions. Significant statistic changes in color parameters ΔL , Δa , Δb of the reline resin DPI, Ufi Gel Hard And Kooliner were also observed when dentures were microwaved. The color stability of the reline resin was influenced by time, regardless of disinfection or non disinfection. Significant statistic changes in color deviation ΔE was observed for both the treatment i.e Microwaved and Chemical Disinfectant. The color stability deviation value ΔE significantly increased maximum for chemical disinfectant, least for Control group and intermediate for microwaved group. The results showed that microwaved specimens have higher color change than specimens did not microwave after 15 days of time interval. Ufi Gel showed the highest deviation ΔE and Control Group showed the lowest deviation according to results.

4. DISCUSSION

Prostheses debased with pathogenic microorganisms fill in as a potential wellspring of

contamination transmission among patients and dental staff [20,21]. To avoid cross-defilement, prostheses ought to be totally purified before being sent to the research center and before insertion [12,17]. Several techniques for cleansing have been prescribed to guarantee disease control in dental practice. Many people do not clean their dentures satisfactorily and may misuse chemical cleansers leading to the deterioration of acrylic dentures. This in vitro assessed the color stability of Kooliner GC, UFI Gel hard and DPI when drenched in chemical disinfectant (Sodium Perborate monohydrate), when microwaved in comparison with control group where samples are only immersed in water without the use of any disinfection method at different intervals of time to check the color stability. The invalid speculation that there would be no impact of denture chemical and microwave sterilization on shading security of relining material was evaluated. There was a perceptible color stability change in control group with time. ΔL displayed a huge diminishing after some time for Control aggregate, which shows a fading (brightening) impact of reline material. Discoloration of resin based materials may be caused by intrinsic or extrinsic factors. Intrinsic factors are related to internal alterations in material resulting from physicochemical reactions or residual monomer oxidation [5]. Thus the initiator, quantity and type of monomer and [22] the polymerisation efficiency may affect the color stability of resin based materials. Furthermore, extrinsic factors that may influence the color change include adsorption, absorption and surface roughness of the denture [6]. The discoloration of polymeric materials may originate from a wide array of sources including superficial absorption and endogenous irreversible discoloration attributed to changes in chemical structure of the material surface or outer layer with time. There is superficial diffusion of hydrophilic colorings, and internal or bulk discoloration derived from incomplete conversion of photo initiators and unconverted C=C bond [23,24]. The increase of color change of the UFI gel could be attributed to the initiator, quantity and type of monomer and the polymerisation efficiency can affect the color stability of resin based materials few relining material demand less chemical disinfection concentration as compared to other hence according to this study we were able to know that UFI Gel due to highest number of unconverted C=C bond react fast and causes color change with highest deviation. The susceptibility to color change of the resin UFI gel, Kooliner and DPI

evaluated in this study could be attributed to both intrinsic and extrinsic factors. According to UFI Gel showed the highest ΔE with time and It was also noticed that Chemical disinfectant showed the highest ΔE and Control group the lowest due to less affect by extrinsic and intrinsic factors [25] Hence, Concentration of chemical disinfection and residual molecule present in the relining material type combination is accountable for color stability variation. The results of present study are in agreement with these findings. Therefore, further studies should consider the evaluation of other concentrations according to relining material used. The dentist should check for the concentration quantity for disinfection. And manufacturer should also mention about the concentration of chemical disinfection to be used for disinfection of relining material. The color stability of the reline resin was influenced by time, regardless of disinfection or non-disinfection. This could be credited to extraneous components like water assimilation and adsorption and furthermore to hydrophilic nature of material and characteristic variables which cause inner adjustments in material coming about because of physicochemical responses or lingering monomer oxidation [26]. Although the disinfectant arrangements utilized in this examination have been shown for denture biofilm control, patients ought to be educated concerning the likelihood of reline materials recoloring in long haul, paying little mind to the utilization or not of disinfectant arrangements.

5. CONCLUSION

Hence, the microwave disinfection method should be considered a better method for disinfection as compared to Chemical disinfection because of absence staining agent present. Chemical disinfection may have accelerated the content of residual monomer, which took place with time.

CONCENT AND ETHICAL APPROVAL

As per university standard guideline participant consent and ethical approval has been collected and preserved by the authors.

ACKNOWLEDGEMENT

I would like to extend my sincere gratitude to the Head of Department of Prosthodontics Dr Archana Nagpal, my guide Dr Rajeev Gupta and my co guide Dr. Vishal Katna for their guidance and wisdom.

COMPETING INTERESTS

Authors have declared that no competing interests exist.

REFERENCES

1. Machado AL, et al. Hardness of denture base and hard chair-side relined acrylic resins. *J Appl Oral Sci.* 2005;13(3):291-5.
2. Webb BC, Thomas CJ, Whittle T. A 2 year study of candida associated denture stomatitis treatment in aged care subjects. *The Gerodontology Association.* 2005;22: 168-76.
3. Moffa BE, Giampaolo ET, Izumida FE, Pavarina AC, Machado AL, Vergani CE. Color stability of relined dentures after chemical disinfection. A randomised clinical trial. *J of Dentistry.* 2011;39s:e65-71.
4. Quinn DM. The effectiveness, in vitro, of miconazole and ketoconazole combined with tissue conditioners in inhibiting the growth of *Candida albicans*. *J Oral Rehabil.* 1984;12(2):177-82.
5. Campanha NH, Giampaolo ET, Pavarina AC, Machado AL, Carlos IZ, Vergani CE. Cytotoxicity of hard chairside relined resins: Effect of microwave irradiation and water bath postpolymerization treatments. *Int J Prosthodont.* 2006;19:195-201.
6. Moffa EB, et al. Color stability of relined resin after microwave disinfection and immersion in drinks for different periods. *J of International Oral Health.* 2016;8:63-70.
7. Basso MFM, Giampaolo ET, Vergani CE, Machado AL, Pavarina AC, Ribeiro RC. Influence microwave disinfection on the dimensional stability of denture relined polymers. *J of Prosthodontics.* 2010;9: 364-68.
8. Wagner DA and Pipko DJ. The effect of repeated microwave irradiation on the dimensional stability of a specific acrylic denture resin. *Journal of Prosthodontics.* 2015;24:25-31.
9. Blagojevic V, Murphy VM. Microwave polymerization of denture base materials. A comparative study. *J Oral Rehabil.* 1999; 26(10):804-8.
10. Mima, et al. Effect of Different Exposure times on Microwave Irradiation on the Disinfection of a Hard Chairside Relined Resin. *J of Prosthodontics.* 2008;17:312-17.
11. Sahin C, Ayyildiz S, Ergin A, Uzun G. Effect of chemical denture cleanser on microorganisms over heat polymerized acrylic resin. *Afr. J. Dent.* 2013;005-009.
12. Silva MM, Vergani CE, Giampaolo ET, Neppelenbroek KH, Spolidorio DMP, Machado AL. Effectiveness of microwave irradiation on the disinfection of complete dentures. *The Int Journal of Prosthodontics.* 2006;19:288-92.
13. Karin Hermans Neppelenbroek, et al. Hardness of heat-polymerized acrylic resins after disinfection and long-term water immersion. *J Prosthetic Dent.* 2005; 93(2): 171-176.
14. Water MGJ, Williams DW, Jagger RG and Lewis MAO. Adherence of *Candida albicans* to experimental denture soft lining materials. *Journal of Prosthodontics.* 1977;3:306-12.
15. Chow CKW, Matear DW, Lawrence HP. Efficacy of antifungal agents in tissue conditioners in treating candidiasis. *Gerodontology.* 1999;16(2):110-8.
16. Machado AL, Giampaolo ET, Vergani CE, Souza JFD, Jorge JH. Changes in roughness of denture base and relined materials by chemical disinfection or microwave irradiation. Surface roughness of denture base and relined material. *J Appl Oral Sci.* 2011;19:521-8.
17. Machado AL, Breeding LC, Vergani CE, Perez LEDC. Hardness and surface roughness of relined and denture base acrylic resins after repeated disinfection procedures. *J Prosthet Dent.* 2009;102: 115-21.
18. Tanaka K, et al. Coding visual images of objects in the inferotemporal cortex of the macaque monkey. *J Dent.* 1991;16(7):134-36.
19. Truhlar MR, Shay K, Sohnle P. Use of a new assay technique for quantification of antifungal activity of nystatin incorporated in denture liners. *J Prosthet. Dent.* 1994; 71(5): 517-24.
20. Thomas CJ, Nutt GM. The *in vitro* fungicidal properties of Visco-gel, alone and combined with nystatin and amphotericin B. *J Oral Rehabil.* 1978; 5(2):167-72.
21. Addy M, Roberts WR. Comparison of the *in vivo* and *in vitro* antibacterial properties of antiseptic mouthrinses containing chlorhexidine, alexidine, cetyl pyridinium chloride and hexetidine. Relevance to

- mode of action. J Clin Periodontol. 1981; 8(4):295-310.
22. Arima T, Murata H, Hamada T. Analysis of composition and structure of hard auto polymerizing relined resins. Journal of Oral Rehabilitation. 1996;23:346-52.
23. Theodore Eliades, et al. Color Stability of Orthodontic Adhesive Resins. The Angle Orthodontist. 2004;74(3):391-393.
24. Baker S, Brooks SC, Walker DM. The release of residual monomeric methyl methacrylate from acrylic appliances in the human mouth: An assay for monomer in saliva. J Dent Res. 1988;67(10):1295-9.
25. Chaing BK, et al. Polymers in the service of Prosthetic dentistry. J Dent. 1984;12(3): 203-14.
26. Polyzois GL, Zissis AJ, Yannihaus SA. The effect of disinfection methods on the dimensional stability, flexural properties, and microhardness of a heat-polymerized denture acrylic resin. J Dent Res. 1995; 65(9):135-38.

© 2019 Jabeen et al.; This is an Open Access article distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/4.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Peer-review history:

*The peer review history for this paper can be accessed here:
<http://www.sdiarticle3.com/review-history/48257>*